

## PFOA Free

A PTFE thickened, light viscosity, completely fluorinated grease possessing very wide temperature capability, excellent plastic and elastomer compatibility and resistance to aggressive chemicals.

Lubricant Properties			Typical Value	Test Method
Recommended Service Range (°C)			-70 to 200	
Thickener			PTFE	
Base Oil			Perfluoropolyether	
(Uniflor 8710)	Type			
	Kinematic Viscosity	40°C	26 cSt	ASTM D-445
		-40°C	3000 cSt	ASTM D-445
	Viscosity Index		179	ASTM D-2270
	Flash Point		None, Non-Flammable	ASTM D-92
	Pour Point	°C	-76	ASTM D-97
Typical Properties of the Grease			Typical Value	Test Method
Color, Appearance			White, Smooth	
Penetration (1/10 mm)	Unworked		276	ASTM D-217
	Worked	60X	288	ASTM D-217
	NLGI Grade		2	ASTM D-217
Density		25°C	1.9 g/cm <sup>3</sup>	NYE CTM
Oil Separation	24 hour(s)	100°C	8	ASTM D-6184
Evaporation	24 hour(s)	100°C	0.7 %	ASTM D-972

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product.

(1601)