# Technical Data Sheet

# Aerospace Sealants



## **CA 1010 Mastinox Chromate Free Jointing Compound**

#### **Description**

CA 1010 is a non-curing, non-chromate corrosion inhibitive compound. It has a service temperature of -54°C (-65°F) to 160°C (320°F). This material acts as an effective barrier against the common causes of corrosion on aluminium alloys or between dissimilar metals. The compound remains permanently mastic afte prolonged exposure to aircraft fuels, both jet fuel and aviation gas.

CA 1010 is a one-part, polyester compound. The material is thixotropic paste suitable for application by brush or spatula.

#### **Application properties (typical)**

Colour off white

Appearance

Uniform composition, no lumps or separated material

Viscosity,

(Brookfield #6 @ 20 rpm) Pa.s (poise)

84 (840)

#### **Performance properties (typical)**

Cured specific gravity	1.37
Non-volatile content, %	89
Pigent contents, %	43
Fineness of grind, Hegman	> 5
Flash point °C (°F) Closed cup (SETA)	24 (75)
Solubility in water@ 23°C (7 °F), %	2

Exposure to heat @ 40°C (104°F) 95 % R.H for 1000 hours

- aluminum / stainless steel easy removal, no corrosion easy removal, no corrosion

Exposure to dry heat @ 120°C (250°F)

For 1000 hours easy removal, still tacky

Chemical resistance

No swelling, loss of adhesion or film failure After 7 days at 60°C (140°F) in:

- AMS2629 type 1
- AMS3020
- MIL-PRF-83282

Corrosion test by galvanic cell method
No signs of corrosion or sealant deterioration for:
Aluminum / Titanium couple, 2 weeks
Aluminum / Stainless steel couple, 2 weeks

**Note:** The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

#### **Surface preparation**

Immediately before applying sealant to primed substrates, the surfaces should be cleaned with solvents. Contaminants such as dirt, grease, and/or processing lubricants must be removed prior to sealant application. A progressive cleaning procedure should be employed using appropriate solvents and a new lint-free cloth conforming to AMS3819. (Reclaimed solvents or tissue paper should not be used).

Always pour solvent on the cloth to avoid contaminating the solvent supply. Wash one small area at a time. It is important that the surface is dried with a second clean cloth prior to the solvent evaporating to prevent the redeposition of contaminants on the substrate.

Substrate composition can vary greatly. This can affect sealant adhesion. It is recommended that adhesion characteristics to a specific substrate be determined prior to application on production parts or assemblies.

For a more thorough discussion of proper surface preparation, please consult the SAE Aerospace Information Report AIR 4069. This document is available through SAE, 400 Commonwealth Avenue, Warrendale, PA 15096-0001.

#### **Packing options**

CA 1010 is supplied in 1 part 6 oz. Semco® cartridges.

#### **Mixing instructions**

CA 1010 is supplied in a 1 part 6 oz. Semco® cartridge. Mixing is not required.

#### Storage life

The storage life of CA 1010 is at least 12 months when stored at temperatures below 80°F (27°C) in original, unopened containers.

### **CA 1010 Mastinox Chromate Free Jointing Compound**

#### **Health precautions**

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations.

An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

For emergency medical information call: 1-800-228-5635.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call: 1-800-AEROMIX (2376649).

#### Permapol and Semkit are trademarks of PRC-DeSoto International Inc., registered with the U.S. Patent Office.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PRC-DeSoto International, Inc. 12780 San Fernando Road Sylmar, CA 91342 Telephone (818) 362-6711 Toll Free (800) AEROMIX www.ppgaerospace.com

Issue Date: 02/22 Supersedes: 01/17

Lit: 4437